

Attenuation Membrane for Contaminated Land Specification 1mm

Tested Property	Unit	Test Method	Value
Thickness	mm	UNE EN 1849-2	1.00
Confidence level 95%	%	-	Tolerance ± 6
Confidence level 90%	%	-	Tolerance ± 4

Tensile Properties (*)	Unit	Test Method	Value
Tensile strength at break	N/mm	UNE-EN ISO 527 (type V)	31 (26)
Elongation at break	%	UNE-EN ISO 527 (type V)	800 (>750)
Tear Resistance	N	ISO 34-1	≥ 100
Puncture Resistance	KN	UNE-EN ISO 12236	2.50
Exploding Resistance	%	Pr EN 14151	<15
Dimensional Stability	%	UNE EN ISO 14632 (100-C, 1h)	± 1.5

	Parameter	Units	1.00
PRESENTATION (Standard Sizes)	Roll Width	m	6
	Roll Length	m	210
	Surface	m ²	1260

Unit 2 Andoversford Industrial Estate, Andoversford, Cheltenham, GL54 4LB

Tel: +44(0)1242 821678

Fax: +44 (0) 1242 821510

Email: sales@hewitech.co.uk

Web: www.hewitech.co.uk