

### Attenuation Standard Membrane Specification .75mm

Tested Property	Unit	Test Method	Value
Thickness	mm	UNE EN 1849-2	0.75
Confidence level 95%	%	-	Tolerance $\pm 6$
Confidence level 90%	%	-	Tolerance $\pm 4$

Tensile Properties (*)	Unit	Test Method	Value
Tensile strength at break	N/mm	UNE-EN ISO 527 (type V)	23(19)
Elongation at break	%	UNE-EN ISO 527 (type V)	$\geq 700$
Tear Resistance	N	ISO 34-1	$\geq 75$
Puncture Resistance	KN	UNE-EN ISO 12236	2.10
Exploding Resistance	%	Pr EN 14151	<15
Dimensional Stability	%	UNE EN ISO 14632 (100-C, 1h)	$\pm 1.5$

	Parameter	Units	0.75
<b>PRESENTATION</b> <b>(Standard Sizes)</b>	Roll Width	m	6/6.30
	Roll Length	m	280
	Surface	m <sup>2</sup>	1680/1764

Unit 2 Andoversford Industrial Estate, Andoversford, Cheltenham, GL54 4LB

Tel: +44(0)1242 821678

Fax: +44 (0) 1242 821510

Email: [sales@hewitech.co.uk](mailto:sales@hewitech.co.uk)

Web: [www.hewitech.co.uk](http://www.hewitech.co.uk)